

**CLIENT:** GEOPLAST S.P.A.  
VIA MARTIRI DELLA LIBERTA' 6/8  
35010 GRANTORTO (PD)

**OBJECT:** Factory product control

**TYPE OF SAMPLE:** Molds for ventilated crawl space

**SAMPLE:** Molds H60 base 71x71cm

**FACTORY:** Factory in Grantorto (PD)

**SAMPLING:** Executed by producer

**DELIVERY SAMPLES DATE:** 29-02-08

**TESTS:** 1) Determination of resistance to concentrated load (UNI 9730-3:1990 - D.M. 09/01/96 All. 7 mod.)

**TESTING DATE:** from 14-03-08 to 14-03-08

**PHOTO SAMPLE:**







## TEST 1): DETERMINATION OF RESISTANCE TO CONCENTRATED LOAD (UNI 9730-3:1990 - D.M. 09/01/96 All. 7 mod.)

Procedure: The load was applied with a prismatic section 80x80 mm as requested by the client.  
The load was applied at the center of the upper face up to failure by rupture of the specimens.

Sample	Maximum Load
n°	kN
1	2,0
2	1,9
3	2,1
4	2,0
5	1,9
6	2,1
7	2,0
8	2,1
9	2,2
10	2,0

Monte di Malo, 17-03-08

  
The experimenter  
Dott. Andrea Zanrosso

  
Building Product Sector  
The Director  
dott. geol. Danilo Belli

*This test report refers only to samples tested only and may not be reproduced unless prior written permission of the laboratory.*